



KÖSTER Mautrol Flex 2C

Technical Data Sheet M 262 020

Issued: 2019-09-06

- WZ "MAUTROL" ges. gesch., Deutsches Patentamt, K 50 862

2-component injection liquid for subsequent installation of damp proof horizontal barriers

Features

KÖSTER Mautrol Flex 2C is a two component, water-soluble injection liquid on a silicate-acrylate basis. Due to the cross-linking property of the B-component, KÖSTER Mautrol Flex 2C can also be applied in strongly moisture-penetrated structural members without the necessity of drying the structural member before or after the application. Steel reinforcement is not corroded by KÖSTER Mautrol Flex 2C.

Technical Data

Type of effect narrowing of pores / hydrophobing of pore walls Component A Component B Material base Silicate/acrylate Ester Color Milky Ttransparent 1.03 g / cm³ 1.09 g / cm§ Density components Density mixture 1.07 g / cm³ Pot life approx. 1.0 - 18 hours (depending on dilution) Mixing ratio (by weight)

Fields of Application

KÖSTER Mautrol Flex 2C can be injected using low pressure injection systems in order to subsequently install horizontal barriers in masonry, concrete, and plaster against rising and creeping damp. It can be applied from the inside and from the outside.

Application

In order to install horizontal barriers, holes are drilled at a distance of approx. 10 – 15 cm from each other to a depth of 5 cm less than the thickness of the wall in one or two horizontal rows above ground or in case of an excavation and exterior waterproofing, above the base slab. The diameter of the boreholes depends on the diameter of the packers chosen. After cleaning out the boreholes using pressurized air, the packers are installed. If voids are present in the structural member to be injected, a pre-injection with KÖSTER Mautrol Borehole Suspension is recommended. The boreholes which were filled with KÖSTER Mautrol Borehole Suspension are drilled open again after a setting time of 30 minutes to 3 hours. The A component is mixed with water depending on the moisture content of the masonry using the mixing ratios specified in the table below. The mixture is then mixed with the B component.

The amount of dilution of the A component depends on the moisture content of the masonry according to the following table:

| content of the masonly according to the following table. | | | | | |
|--|------------|----------|------------|----------|--|
| Moisture | A comp. M% | Water M% | B comp. M% | Gel time | |
| content M% | | | | | |
| 0 - 5 % | 1 | 10 | 1 | 18 hrs. | |
| 5 - 10 % | 1 | 7 | 1 | 10 hrs. | |
| 10 - 15 % | 1 | 5 | 1 | 6 hrs. | |
| Greater than | 11 | 4 | 1 | 4 hrs. | |
| 15 % | | | | | |

(+ 20 °C)

Attention: Never mix the components undiluted!

The mixture is injected using suitable injection equipment (airless or piston pump) via packers until a complete saturation of the masonry is achieved. This can be done by single injections or with injection batteries. Subsequent injections are possible even after the end of the gel-time. After the injection, the packers are removed and the boreholes are closed with KÖSTER Mautrol Borehole Suspension. A component which is diluted with water can be stored for 2 months. Diluted material which has already been mixed with B component reacts within the gel-time stated above.

Consumption

Approx. 0.2 kg/m per cm wall thickness

Cleaning

Clean tools immediately after use with water.

Packaging

M 262 020 20 kg combipackaging Comp. A 10 kg jerrycan Comp. B 10 kg jerrycan

Storage

Store the material cool but frost-free; in originally sealed packages it can be stored for a minimum of 1 year.

Safety

Wear protective gloves and goggles when processing the material. When carrying out injection works, make sure to protect the surroundings from injection material that may be discharged from the wall, packers, boreholes, etc. due to the pressurized mode of injection or accidentally. Do not stand directly behind the packers during injection. Observe all governmental, state, and local safety regulations while processing the material.

Related products

| KÖSTER Impact Packer 12 mm x 70 mm | Prod. code IN 903 001 |
|--|-----------------------|
| KÖSTER Superpacker 13 mm x 115 mm | Prod. code IN 915 001 |
| CH | |
| KÖSTER One-Day-Site Packer 13 mm x | Prod. code IN 922 001 |
| 120 mm PH | |
| KÖSTER 1C Injection Pump | Prod. code IN 929 001 |
| KÖSTER Loka Handpump | Prod. code IN 952 001 |
| KÖSTER Hand Pump without manometer | Prod. code IN 953 001 |
| KÖSTER Hand Pump with manometer | Prod. code IN 953 002 |
| KÖSTER Footpump | Prod. code IN 958 001 |
| KÖSTER Mautrol Borehole Suspension | Prod. code M 150 024 |
| KÖSTER Mautrol 2C | Prod. code M 261 |
| KÖSTER Fine Plaster | Prod. code M 655 025 |
| KÖSTER Restoration Plaster Grey | Prod. code M 661 025 |
| KÖSTER Restoration Plaster White | Prod. code M 662 025 |
| KÖSTER Restoration Plaster White/Fast | Prod. code M 663 |
| KÖSTER Restoration Plaster White/Light | Prod. code M 664 020 |

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

KÖSTER Mautrol Flex 2C 1/1